



TechResin[®] 0795

High Density Polyethylene (HDPE) Resin for Injection Molding

TechResin[®] 0795 is a hexene based HDPE injection molding resin designed for toughness and good impact strength. TechResin[®] 0795 offers excellent stiffness-toughness balance ideally recommended for applications requiring physical performance and a good impact.

TechResin[®] 0795 meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520 for food packaging, covering safe use of polyolefin articles intended for direct food contact.

Suggested Applications:

Industrial Components Industrial Closures Automotive Components

Waste Carts Recreational Vehicle Components

Nominal Physical Properties:

PROPERTY*	ASTM TEST METHOD	ENGLISH		SI	
		Unit	Value	Unit	Value
Density	D1505	g/cm ³	0.952	g/cm ³	0.952
Melt Index, (190°C/2.16kg)	D1238	g/10 min.	7.0	g/10 min.	7.0
Tensile Strength at Yield	D638	psi.	3900	MPa	26.9
Tensile Yield Elongation	D638	%	8.0	%	8.0
Flexural Modulus (2% Secant)	D790B	psi.	160,000	MPa	1100
Environmental Stress Crack Resistance (100% Igepal, 50°C, F50)	D1693	hr	20	hr	20
Deflection Temperature Under Load (66psi)	D648	°F	164	°C	73
Shore Hardness (Shore D)	D2240	-	68	-	68
Vicat Softening Temperature	D1525	°F	257	°C	125

Note: All properties were derived from compression molded specimens. Actual properties may vary depending on operating conditions and additive packages. Properties are not intended to be used as specifications.

MDT does not guarantee reproduction of these results. This is not a Certificate of Analysis and the customer is responsible for testing and confirming the Material Properties before making commercial use of the product to ensure that the product is fit for the intended application and that the product can be used, and any waste material disposed of, safely, properly, and legally based on the customer's or other's circumstances. Determination of the suitability and fitness of the product for any particular application is the sole responsibility of the purchaser of the product. This information is solely intended for informational purposes. This material confirmation relates solely to the product listed above and not as incorporated in any product or used in any process. Material Difference Technology makes no warranty or representation of any kind, regarding the information given or the products described, and expressly disclaims all implied warranties and conditions of quality, merchantability and suitability or fitness for a particular purpose. The customer or other user of the product assumes all risk and liability arising out of the use of the product, whether used alone or in combination with other materials. The presence absence or lack of information herein with respect to any particular international, national, federal, state or local law, statute, regulation, order or rule should not be construed to mean that product is regulated under, complies with or is exempt from such international, national, federal state or local law, statute, regulation, order or rule.