

TechResin[®] 1095

Extra High Molecular Weight Hexene Copolymer

TechResin[®] 1095 has good melt strength, excellent stress crack resistance, good rigidity, and excellent impact strength even at low temperatures. These properties make TechResin[®] 1095 an excellent resin for large part blow molding applications.

TechResin[®] 1095 meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520 for food packaging, covering safe use of polyolefin articles intended for direct food contact.

Suggested Applications:

Blow Molded...

55-Gallon Shipping Containers
Gasoline Tanks
Agricultural Chemical Tanks

Extruded...

Pallets
Large Formed Parts
Corrugated Pipes (Certified to AASHTO M294)
Conduit Pipes (Meets ASTM F2160)

Nominal Physical Properties:

PROPERTY*	ASTM TEST METHOD	English		SI	
		UNIT	VALUE	UNIT	VALUE
Density	D1505	g/cc	0.948	g/cc	0.948
Melt Index, Condition E, 190°C/21.6 kg (HLMI)	D1238	g/10 min	10.0	g/10 min	10.0
Environmental Stress Crack Resistance (ESCR) Condition B, F ₅₀ (100% Igepal)	D1693	h	>1000	h	>1000
Tensile Yield Strength 2" (50 mm) per min.	D638 Type IV	psi.	3600	MPa	25
Ultimate Elongation 2" (50 mm) per min.	D638 Type IV	%	>600	%	>600
Brittleness Temperature	D746	°F	<-131	°C	<-91
Flexural Modulus	D790	psi.	170,000	MPa	1172

* Physical properties reported herein were determined on compression molded specimens prepared in accordance with Procedure C of ASTM D4703, Annex A1.

The nominal properties reported herein are typical of the product but do not reflect normal testing variance and therefore should not be used for specification purposes.

Published 06/01/01, Revised 06//2022

MDT does not guarantee reproduction of these results. This is not a Certificate of Analysis and the customer is responsible for testing and confirming the Material Properties before making commercial use of the product to ensure that the product is fit for the intended application and that the product can be used, and any waste material disposed of, safely, properly, and legally based on the customer's or other's circumstances. Determination of the suitability and fitness of the product for any particular application is the sole responsibility of the purchaser of the product. This information is solely intended for informational purposes. This material confirmation relates solely to the product listed above and not as incorporated in any product or used in any process. Material Difference Technology makes no warranty or representation of any kind, regarding the information given or the products described, and expressly disclaims all implied warranties and conditions of quality, merchantability and suitability or fitness for a particular purpose. The customer or other user of the product assumes all risk and liability arising out of the use of the product, whether used alone or in combination with other materials. The presence absence or lack of information herein with respect to any particular international, national, federal, state or local law, statute, regulation, order or rule should not be construed to mean that product is regulated under, complies with or is exempt from such international, national, federal state or local law, statute, regulation, order or rule.