

## TechResin® 5620H

### *Homopolymer for Appliance Applications*

TechResin® 5620H is a highly isotactic, homopolymer polypropylene designed for consumer products and appliance applications requiring long-term heat-aging resistance and flexural endurance.

TechResin® 5620H has earned a UL continuous service rating of 65°C with recognition for typical use in laundry equipment.

This material is free of animal-derived content.

### Typical Properties of this Commercial Grade

Property	Test Method	Typical Values	
		English	SI
Melt Flow Rate, I <sub>2</sub> @ 230°C	ASTM D1238	2.0 g/10 min	2.0 g/10 min
Density	ASTM D1505	0.9 g/cm <sup>3</sup>	0.9 g/cm <sup>3</sup>
Tensile Strength at Yield (50 mm/min)	ASTM D638	5,000 psi	34 MPa
Elongation at Yield (50 mm/min)	ASTM D638	10 %	10 %
Flexural Modulus (1.3 mm/min), 1% Secant	ASTM D790	200,000 psi	1379 MPa
Notched Izod Impact Strength @ 73°F	ASTM D256A	1.0 ft-lb/in	53 J/m
Heat Deflection Temperature @ 66 psi	ASTM D648	212 °F	100 °C

*Note: Specimens were injection molded according to the conditions specified in ASTM D4101.*

*Data for representative purposes only; not to be construed as product specification.*

*Published 5/05, Revised 5/13*