

## TechResin<sup>®</sup> 5711A

### ***Impact Copolymer for Injection Molding***

TechResin<sup>®</sup> 5711A is a medium impact copolymer polypropylene characterized by easy mold flow, physical property balance and excellent dimensional stability. It has found use in applications including closures, housewares, small appliances, and battery cases and lids.

TechResin<sup>®</sup> 5711A meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact.

This material is free of animal-derived content.

### **Typical Properties of this Commercial Grade**

Property	Test Method	Typical Values	
		English	SI
Melt Flow Rate, I <sub>2</sub> @ 230°C	ASTM D1238	10 g/10 min	10 g/10 min
Density	ASTM D1505	0.9 g/cm <sup>3</sup>	0.9 g/cm <sup>3</sup>
Tensile Strength at Yield (50 mm/min)	ASTM D638	3,650 psi	25 MPa
Elongation at Yield (50 mm/min)	ASTM D638	7 %	7 %
Flexural Modulus (1.3 mm/min), 1% Secant	ASTM D790	165,000 psi	1138 MPa
Notched Izod Impact Strength @ 73°F	ASTM D256A	2.5 ft-lb/in	133 J/m
Rockwell Hardness	ASTM D785	100 R Scale	100 R Scale

*Note: Specimens were injection molded according to the conditions specified in ASTM D4101.*

*Data for representative purposes only; not to be construed as product specification.*

*Published 2/01, Reviewed 5/13*