

TechResin[®] 57200

Impact Copolymer for Appliance Applications

TechResin[®] 57200 is a medium impact copolymer polypropylene characterized by easy mold flow, physical property balance and excellent dimensional stability. It is designed for consumer products and appliance applications requiring long-term heat-aging resistance and flexural endurance.

TechResin[®] 57200 has earned a UL continuous service rating of 110°C with recognition for typical use in laundry equipment.

This material is free of animal-derived content.

Typical Properties of This Commercial Grade

Property	Test Method	Typical values	
		English	SI
Melt Flow Rate, I2 @ 230°C	ASTM D1238	20 g/10 min	20 g/10 min
Density	ASTM D1505	0.9 g/cm ³	0.9 g/cm ³
Tensile Strength at Yield (50 mm/min)	ASTM D638	3,900 psi	27 MPa
Elongation at Yield (50 mm/min)	ASTM D638	7 %	7 %
Heat Deflection Temperature @ 66 psi	ASTM D648	214 °F	101 °C
Heat Deflection Temperature @ 264 psi	ASTM D648	133 °F	56 °C
Flexural Modulus (1.3 mm/min), 1% Secant	ASTM D790	175,000 psi	1207 MPa
Notched Izod Impact Strength @ 73°F	ASTM D256A	1.7 ft-lb/in	91 J/m

Note: Specimens were injection molded according to the conditions specified in ASTM D4101.

Data for representative purposes only; not to be construed as product specification.

Published 09/10, Revised 5/14

MDT does not guarantee reproduction of these results. This is not a Certificate of Analysis and the customer is responsible for testing and confirming the Material Properties before making commercial use of the product to ensure that the product is fit for the intended application and that the product can be used, and any waste material disposed of, safely, properly, and legally based on the customer's or other's circumstances. Determination of the suitability and fitness of the product for any particular application is the sole responsibility of the purchaser of the product. This information is solely intended for informational purposes. This material confirmation relates solely to the product listed above and not as incorporated in any product or used in any process. Material Difference Technology makes no warranty or representation of any kind, regarding the information given or the products described, and expressly disclaims all implied warranties and conditions of quality, merchantability and suitability or fitness for a particular purpose. The customer or other user of the product assumes all risk and liability arising out of the use of the product, whether used alone or in combination with other materials. The presence absence or lack of information herein with respect to any particular international, national, federal, state or local law, statute, regulation, order or rule should not be construed to mean that product is regulated under, complies with or is exempt from such international, national, federal state or local law, statute, regulation, order or rule.