

TechResin[®] 5737A

Impact Copolymer - Designed to Meet the Physical Requirements of Automotive Interior Trim

TechResin[®] 5737A is an engineered, medium impact copolymer polypropylene. It was specifically developed to meet the OEM demands for automotive interior trim applications, with proven injection molding economy.

Material has been approved under Ford WSS-M4D638-B, GM16208-T1, DCX MS-DB-500 and Toyota TSM 5514G Class 2 for interior trim applications.

The optimal stiffness and impact balance also provides for utility in industrial applications including bins and crates, and small appliances.

This material is free of animal-derived content.

Typical Properties of this Commercial Grade

Property	Test Method	Typical Values	
		English	SI
Melt Flow Rate, I ₂ @ 230°C	ASTM D1238	35 g/10 min	35 g/10 min
Density	ASTM D1505	0.9 g/cm ³	0.9 g/cm ³
Tensile Strength at Yield (50 mm/min)	ASTM D638	3,400 psi	23 MPa
Elongation at Break (50 mm/min)	ASTM D638	100 %	100 %
Flexural Modulus (1.3 mm/min), 1% Secant	ASTM D790	155,000 psi	1069 MPa
Notched Izod Impact Strength @ 73°F	ASTM D256A	2.5 ft-lb/in	133 J/m
Notched Izod Impact Strength @ 32°F	ASTM D256A	1.5 ft-lb/in	80 J/m
Notched Izod Impact Strength @ 0°F	ASTM D256A	1.2 ft-lb/in	64 J/m
Heat Deflection Temperature @ 66 psi	ASTM D648	207 °F	97 °C
Heat Deflection Temperature @ 264 psi	ASTM D648	126 °F	52 °C
Hardness, Durometer Shore D	ASTM D2340	63 Shore D	

Note: Specimens injection molded according to the conditions specified in ASTM D4101.

Data for representative purposes only; not to be construed as product specification.

Published 9/04. Revised 7/14

MDT does not guarantee reproduction of these results. This is not a Certificate of Analysis and the customer is responsible for testing and confirming the Material Properties before making commercial use of the product to ensure that the product is fit for the intended application and that the product can be used, and any waste material disposed of, safely, properly, and legally based on the customer's or other's circumstances. Determination of the suitability and fitness of the product for any particular application is the sole responsibility of the purchaser of the product. This information is solely intended for informational purposes. This material confirmation relates solely to the product listed above and not as incorporated in any product or used in any process. Material Difference Technology makes no warranty or representation of any kind, regarding the information given or the products described, and expressly disclaims all implied warranties and conditions of quality, merchantability and suitability or fitness for a particular purpose. The customer or other user of the product assumes all risk and liability arising out of the use of the product, whether used alone or in combination with other materials. The presence absence or lack of information herein with respect to any particular international, national, federal, state or local law, statute, regulation, order or rule should not be construed to mean that product is regulated under, complies with or is exempt from such international, national, federal state or local law, statute, regulation, order or rule.